

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
29 December 2004 (29.12.2004)

PCT

(10) International Publication Number
WO 2004/113412 A2

(51) International Patent Classification⁷: C08G 61/02

(74) Agents: DÖRR, Klaus et al.; Industriepark Höchst,
Gebäude F821, 65926 Frankfurt am Main (DE).

(21) International Application Number:
PCT/EP2004/006721

(22) International Filing Date: 22 June 2004 (22.06.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
03014042.0 23 June 2003 (23.06.2003) EP

(71) Applicant (for all designated States except US): COVION
ORGANIC SEMICONDUCTORS GMBH [DE/DE];
65926 Frankfurt am Main (DE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): WALLACE, Paul
[GB/GB]; 11 Redwing Rise, Royston, Hertfordshire SG8
7XU (GB). POUNDS, Thomas [GB/GB]; 97 Arbury
Road, Cambridge CB4 2JD (GB). O'DELL, Richard
[GB/DE]; Jettenstetten 23, 84416 Taufkirchen (DE).
TOWNS, Carl [GB/GB]; Crown Cottage, 192 Silver
Street, Mountfitchet, Stansted, Essex CM24 8HB (GB).
McKIERNAN, Mary [GB/GB]; 12 Lee Close, Cottenham
(GB).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI,
SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, ML, MR, NE, SN, TD, TG).

Published:

— without international search report and to be republished
upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: POLYMER

(57) Abstract: The present invention relates to new semiconductive oligomers and polymers, a process for their manufacture and their use in thin film electronic and optical devices, such as organic light emitting diodes (OLED) and photovoltaic devices, e.g. solar cells and photodetectors.

WO 2004/113412 A2

Polymer

Field of the Invention

This invention relates to semiconductive oligomers and polymers, their synthesis and use in thin film electronic and optical devices.

Background of the Invention

Semiconducting organic materials are attracting a great deal of interest due to their processability and the broad spectrum of optical and electronic properties that may be selected according to the structure of the organic material.

One application of such materials is in switching devices, in particular as organic field effect transistors as described in, for example, Adv. Mater. 1998 10(5), 365-377.

Another application is in opto-electrical devices using a semiconducting organic material for light emission (an organic light emitting device or "OLED") or as the active component of a photocell or photodetector (a "photovoltaic" device). The basic structure of these devices is a semiconducting organic layer sandwiched between a cathode for injecting or accepting negative charge carriers (electrons) and an anode for injecting or accepting positive charge carriers (holes) into the organic layer.

In an organic electroluminescent device, electrons and holes are injected into a layer of electroluminescent semiconducting material where they combine to generate excitons that undergo radiative decay. Holes are injected from the anode into the highest occupied molecular orbital (HOMO) of the electroluminescent material; electrons are injected from the cathode into the lowest unoccupied molecular orbital (LUMO) of the electroluminescent material. In WO 90/13148 the organic light-emissive material is a polymer, namely poly(p-phenylenevinylene) ("PPV"). This class of device is commonly known as a polymer light emitting device (PLED). In US 4,539,507 the organic light-emissive material is of the class known as small molecule materials, such as (8-hydroxyquinoline) aluminium ("Alq₃").


One alternative to PPVs are 2,7-linked polyfluorenes as disclosed in EP 0842208 which have attracted attention because of their advantage of solution processability, such as suitability for inkjet printing. Furthermore, fluorene monomers with appropriate leaving groups are amenable to Suzuki or Yamamoto polymerisation. Suzuki polymerisation in particular affords a great deal of control over the regioregularity and therefore the properties of the polymer. Fluorene repeat units may therefore be used as a "building block" in creating co-polymers with a wide range of charge transporting and / or emissive properties.

However, there are a number of disadvantages associated with polyfluorenes which have led to a search for alternative electron transporting and light emitting units. These disadvantages include the tendency of polyfluorenes to aggregate and the fact that when blue light emission occurs from fluorene based polymers the emission

does not occur in the region of the electromagnetic spectrum in which the human eye is most sensitive.

One alternative to fluorene repeat units are trans-indenofluorene repeat units (illustrated below) as disclosed in, for example, *Macromolecules* 2000, 33(6), 2016-2020 and *Advanced Materials*, 2001, 13, 1096-1099.

Polymers comprising the tetraoctyl trans-indenofluorene unit are described as having




a bathochromically shifted emission wavelength which leads to a blue emission colour matched to the sensitivity of the human eye. However, poly(trans-indenofluorenes) have a lower conductivity than corresponding polyfluorenes.

It is therefore an object of the invention to provide a repeat unit that possesses the advantages of trans-indenofluorene over fluorene without suffering from loss of conduction.

Summary of the invention

The present inventors have surprisingly found that oligomers or polymers comprising cis-indenofluorene repeat units have comparable or better conduction than corresponding oligomers or polymers comprising fluorene repeat units. Furthermore, the present inventors have surprisingly found that oligomers or polymers comprising cis-indenofluorene repeat units are blue-shifted relative to the corresponding oligomers or polymers comprising trans-indenofluorene repeat units.

Accordingly, in a first aspect the invention provides an oligomer or polymer comprising an optionally substituted first repeat unit of formula (Ir):



wherein R^1 , R^2 , R^3 and R^4 , which may be the same or different, are independently selected from hydrogen or a substituent and two or more of R^1 , R^2 , R^3 and R^4 may be linked to form a ring.

Without wishing to be bound by any theory, it is believed that locating groups R^1 , R^2 , R^3 and R^4 on the same side of the repeat unit backbone enables close packing of oligomers or polymers containing the backbone, leading to improved conductivity, as compared to trans-indenofluorene repeat units which have two substituent groups on

one side of the repeat unit and two substituent groups on the opposite side of the backbone. Furthermore, the present inventors have found that there is a small twist within the repeat unit of formula (Ir) which is believed to be due to steric interactions between groups R^1 and R^2 and groups R^3 and R^4 . This twist, which is not present in the corresponding trans-indenofluorene repeat unit, renders the cis-indenofluorene unit of formula (Ir) less prone to aggregation than a corresponding trans-indenofluorene unit. Finally, this twist also blue-shifts the colour of emission of oligomers or polymers comprising the repeat unit of formula (I) as compared to oligomers or polymers comprising repeat units of trans-indenofluorenes.


Certain substituents R^1 , R^2 , R^3 and R^4 may modify the properties of the repeat unit, and therefore the polymer, such as its solubility, electron affinity or glass transition temperature (T_g). Therefore, it is preferred that each R^1 , R^2 , R^3 and R^4 is independently selected from the group consisting of optionally substituted alkyl, alkoxy, aryl, or heteroaryl. More preferably, at least one of R^1 , R^2 , R^3 and R^4 is optionally substituted phenyl or optionally substituted C_{1-20} alkyl.

Particularly preferred substituents are C_{1-20} alkyl or alkoxy, in particular branched alkyl or n-alkyl, such as n-octyl, as solubilising substituents; optionally substituted phenyl or oligophenyl (e.g. biphenyl or terphenyl) as T_g increasing substituents, in particular unsubstituted phenyl, phenyl substituted with alkyl or alkoxy to improve solubility and phenyl substituted with fluorine, fluoroalkyl, perfluoroalkyl to increase electron affinity; and optionally substituted, electron deficient heteroaryls in particular pyridine, pyrimidine and triazine, each of which may be unsubstituted or substituted with substituents listed as for phenyl above.

Asymmetry within the polymer may be desirable in order to minimise the possibility of aggregation. Therefore, it is preferred that at least one of R^1 , R^2 , R^3 and R^4 is different from at least one other of R^1 , R^2 , R^3 and R^4 . In one particularly preferred embodiment, R^1 and R^2 are both optionally substituted alkyl and R^3 and R^4 are both optionally substituted aryl. In another particularly preferred embodiment, R^1 and R^3 are both optionally substituted alkyl and R^2 and R^4 are both optionally substituted aryl.

Appropriate selection of the four substituents R^1 , R^2 , R^3 and R^4 enables greater control over the properties of the oligomer or polymer as compared to corresponding fluorenes wherein there are only two such substitution positions. Further modification of the properties of the repeat unit of the invention may be achieved by substitution of one or more of the phenyl groups of the repeat unit of formula (Ir). Preferably, such substitution takes the form of a repeat unit of formula (II):


(II)



wherein at least one of R^7 and R^8 represents a substituent, and R^7 and R^8 together may form a ring.


In one preferred embodiment, R^7 and R^8 are both substituents and are the same or different. Preferred substituents R^7 and R^8 are optionally substituted alkyl, alkoxy, aryl, or heteroaryl; particularly preferred substituents R^7 and R^8 are as described above with reference to R^1 , R^2 , R^3 and R^4 .

Preferably, the first repeat unit is linked through the 2- and 9-positions as shown below (because this maximises conjugation through the repeat unit).



The polymer, according to the invention may be a homopolymer or a co-polymer. Where the polymer is a co-polymer wide range of properties may be accessed by appropriate selection of co-repeat unit or co-repeat units. Therefore, the oligomer or polymer preferably comprises a second repeat unit. Preferably, the second repeat unit comprises an aryl group that is directly conjugated to the first repeat unit. More preferably, the second repeat unit is selected from optionally substituted aryl, heteroaryl and triarylamine repeat units.

In a second aspect, the invention provides an optionally substituted monomer of formula (Im):



wherein R^1 , R^2 , R^3 and R^4 , which may be the same or different, are independently selected from hydrogen or a substituent and two or more of R^1 , R^2 , R^3 and R^4 may be linked to form a ring; and each P represents a polymerisable group.

Advantageous polymerisation techniques include Suzuki and Yamamoto polymerisations which operate via a "metal insertion" wherein the metal atom of a metal complex catalyst is inserted between an aryl group and a leaving group of a monomer. Therefore, each P preferably represents a leaving group capable of participating in a polycondensation mediated by a metal of variable oxidation state.

Preferably, the polycondensation is mediated by a metal insertion.

Preferably, each P is independently selected from halogen; a moiety of formula $-O-SO_2-Z$ wherein Z is selected from the group consisting of optionally substituted alkyl and aryl; or a reactive boron group selected from a boronic acid, a boronic ester

or a borane. Preferred halogens are bromine, chlorine and iodine, more preferably bromine.

In a third aspect, the invention provides a process for preparing an oligomer or polymer comprising the step of oligomerising or polymerising a monomer according to the second aspect of the invention.

In a first preferred embodiment of the third aspect, each P is independently a halogen or a moiety of formula $-O-SO_2-Z$, wherein Z is selected from the group consisting of optionally substituted alkyl and aryl, and the monomer of formula (Im) is oligomerised or polymerised in the presence of a nickel complex catalyst.

In a second preferred embodiment of the third aspect, the monomer of formula (Im) is oligomerised or polymerised with a second aromatic monomer in the presence of a palladium complex catalyst and a base and

- (a) each P is the same or different and comprises a reactive boronic group and the second monomer comprises two reactive groups independently selected from halogen and a moiety of formula $-O-SO_2-Z$, or
- (b) each P independently comprises a halogen or a moiety of formula $-O-SO_2-Z$ and the second monomer comprises two reactive boron groups which are the same or different.


In a third preferred embodiment of the third aspect, one P is a reactive boron group and the other P is a halogen or a moiety of formula $-O-SO_2-Z$.

In a fourth aspect, the invention provides an optical device comprising an oligomer or polymer according to the first aspect of the invention. Preferably, the oligomer or polymer is located between a first electrode for injection of charge carriers of a first type and a second electrode for injection of charge carriers of a second type.


In addition to their applicability in optical devices such as OLEDs or photovoltaic devices, the oligomers or polymers according to the invention may be used in a switching device. Accordingly, in a fifth aspect the invention provides a switching device comprising an oligomer or polymer according to the first aspect of the invention. In a preferred embodiment, this aspect of the invention provides a field effect transistor comprising an insulator having a first side and a second side; a gate electrode located on the first side of the insulator; an oligomer or polymer according to the first aspect of the invention located on the second side of the insulator; and a drain electrode and a source electrode located on the oligomer or polymer.

In a sixth aspect, the invention provides an integrated circuit comprising a field effect transistor according to the fifth aspect of the invention.

In a seventh aspect, the invention provides A method of forming an optionally substituted compound of formula (I):



comprising the step of eliminating LG-H from an optionally substituted compound of formula (Ip):



wherein each LG is the same or different and represents a leaving group.

Suitable leaving groups include halide, -OR, -SR, -OSO₂R and -NR₂ wherein each R independently represents hydrogen or optionally substituted alkyl or aryl. Preferably, each LG is hydroxy.

Preferably, the elimination is performed in the presence of an acid.

Preferably, the acid is polyphosphoric acid.

Preferably, the method comprises the further step of providing a polymerisable group P on each of the outer phenyl rings of the compound of formula (I) or (Ip).

Detailed Description of the Invention

Oligomers and polymers according to the invention may be used as solution processable, electron transporting, hole transporting and / or emissive materials in organic light emitting devices. The invention is described hereinafter with reference to polymers, however it will be appreciated that features described herein may apply equally to oligomers.

The polymers may be prepared by Suzuki polymerisation as described in, for example, WO 00/53656 or WO 03/048225 and Yamamoto polymerisation as described in, for example, T. Yamamoto, "Electrically Conducting And Thermally Stable π -Conjugated Polyarylenes Prepared by Organometallic Processes", Progress in Polymer Science 1993, 17, 1153-1205 or WO 04/022626. For example, in the synthesis of a linear polymer by Yamamoto polymerisation, a monomer having two reactive halide groups P is used. Similarly, according to the method of Suzuki polymerisation, at least one reactive group P is a reactive boron group.

Suzuki polymerisation employs a Pd(0) complex or a Pd(II) salt. Pd(0) complexes are preferred, in particular Pd(0) complexes bearing at least one phosphine ligand such as Pd(Ph₃P)₄. Suzuki polymerisation is performed in the presence of a base, for example sodium carbonate or an organic base such as tetraethylammonium carbonate.

Yamamoto polymerisation employs a Ni(0) complex, for example bis(1,5-cyclooctadienyl)nickel(0).

Suzuki polymerisation may be used to prepare regioregular, block and random copolymers. In particular, homopolymers or random copolymers may be prepared when one reactive group P is a halogen and the other reactive group P is a reactive boron group. Alternatively, block or regioregular, in particular AB, copolymers may be prepared when both reactive groups of a first monomer are boron and both reactive groups of a second monomer are halide.







The monomer according to the invention may be polymerised alone to form a homopolymer or in the presence of one or more co-monomers to form a co-polymer. Possible co-repeat units derived from such co-monomers are outlined below; it will be appreciated that each of these co-repeat units may be derived from a comonomer comprising two polymerisable groups independently selected from halogen (preferably chlorine, bromine or iodine, more preferably bromine), a boronic acid group, a boronic ester group and a borane group.

As alternatives to halogens as described above, leaving groups such as tosylate, mesylate and triflate may also be used.

Where the polymer according to the invention is a co-polymer, one class of co-repeat units is arylene repeat units, in particular: 1,4-phenylene repeat units as disclosed in J. Appl. Phys. 1996, 79, 934; fluorene repeat units as disclosed in EP 0842208, trans-indenofluorene repeat units as disclosed in, for example, Macromolecules 2000, 33(6), 2016-2020 and spirobifluorene repeat units as disclosed in, for example EP 0707020. Each of these repeat units is optionally substituted. Examples of substituents include solubilising groups such as C₁₋₂₀ alkyl or alkoxy; electron withdrawing groups such as fluorine, nitro or cyano; and substituents for increasing glass transition temperature (T_g) of the polymer such as bulky groups, e.g. tert-butyl.

A further class of preferred co-repeat units are repeat units comprising one or two amino groups in the repeat unit backbone such as co-repeat units comprising triarylamine groups, in particular repeat units of formulae 1-6:


8




X and Y may be the same or different and are substituent groups. A, B, C and D may be the same or different and are substituent groups. It is preferred that one or more of X, Y, A, B, C and D is independently selected from the group consisting of alkyl, aryl, perfluoroalkyl, thioalkyl, cyano, alkoxy, heteroaryl, alkylaryl and arylalkyl groups. One or more of X, Y, A, B, C and D also may be hydrogen. It is preferred that one or more of X, Y, A, B, C and D is independently an unsubstituted, isobutyl group, an n-alkyl, an n-alkoxy or a trifluoromethyl group because they are suitable for helping to select the HOMO level and/or for improving solubility of the polymer.


Use of trifluoromethyl groups in repeat units of this type is disclosed in WO 01/66618.

A yet further class of co-repeat units include heteroaryl repeat units such as optionally substituted 2,5-thienyl, pyridyl, diazine, triazine,azole, diazole, triazole, oxazole or oxadiazole; or optionally substituted units of formulae 7-19:







8




9




10




11




12




13




14




15




16



17



18



19

wherein R^5 and R^6 are the same or different and are each independently a substituent group. Preferably, one or more of R^5 or R^6 may be selected from hydrogen, alkyl, aryl, perfluoroalkyl, thioalkyl, cyano, alkoxy, heteroaryl, alkylaryl, or arylalkyl. These groups are preferred for the same reasons as discussed in relation to X, Y, A, B, C and D above. Preferably, for practical reasons, R^5 and R^6 are the same.

When used in an OLED, polymers according to the invention possess at least one of hole transporting, electron transporting and emissive properties. Where the polymer has more than one of these properties, different properties may be provided by different segments of a block co-polymer, in particular segments of the polymer backbone as described in WO 00/55927 or pendant groups as described in WO 02/26859. Alternatively, if the polymer of the invention has only one or two of the properties of hole transport, electron transport and emission, it may be blended with one or more further polymers having the remaining required property or properties as described in WO 99/48160.

Polymers according to the invention may be used as active materials in any of the aforementioned optical devices, in particular electroluminescent devices and photovoltaic devices (i.e. photodetectors or photocells). Such optical devices comprise a substrate carrying the polymer located between a positive charge carrying electrode and a negative charge carrying electrode. In forming these devices, the polymer may be deposited from solution by any one of a range of techniques including in particular techniques such as spin-coating, dip-coating, inkjet printing as disclosed in EP 0880303, laser transfer as described in EP 0851714, flexographic printing, screen printing and doctor blade coating.

Optical devices tend to be sensitive to moisture and oxygen. Accordingly, the substrate of the device preferably has good barrier properties for prevention of ingress of moisture and oxygen into the device. The substrate is commonly glass, however alternative substrates may be used, in particular where flexibility of the device is desirable. For example, the substrate may comprise a plastic as in US 6268695 which discloses a substrate of alternating plastic and barrier layers or a laminate of thin glass and plastic as disclosed in EP 0949850.

Although not essential, the presence of a layer of organic hole injection material over the anode is desirable as it assists hole injection from the anode into the layer or layers of semiconducting polymer. Examples of organic hole injection materials include PEDT / PSS as disclosed in EP 0901176 and EP 0947123, or polyaniline as disclosed in US 5723873 and US 5798170.

The cathode is selected in order that electrons are efficiently injected into the device and as such may comprise a single conductive material such as a layer of aluminium. Alternatively, it may comprise a plurality of metals, for example a bilayer of calcium and aluminium as disclosed in WO 98/10621, or a thin layer of dielectric material such as lithium fluoride to assist electron injection as disclosed in, for example, WO 00/48258.

The device is preferably encapsulated with an encapsulant to prevent ingress of moisture and oxygen. Suitable encapsulants include a sheet of glass, films having suitable barrier properties such as alternating stacks of polymer and dielectric as disclosed in, for example, WO 01/81649 or an airtight container as disclosed in, for example, WO 01/19142.



In a practical optoelectronic device, at least one of the electrodes is semi-transparent in order that light may be absorbed (in the case of a photoresponsive device) or emitted (in the case of a PLED). Where the anode is transparent, it typically comprises indium tin oxide. Examples of transparent cathodes are disclosed in, for example, GB 2348316. Where the polymer of the invention is used in a switching device such as a field effect transistor, it will be appreciated that all of the electrodes may be opaque.

The PLED may be a passive matrix or active matrix device.

Examples

Monomer Example

A monomer according to the invention was prepared in accordance with the scheme set out below:


**Monomer 1****Synthesis of Diene, St1.**

1,4-Diphenyl-1,3-butadiene (500g, 2.42 moles) and dimethylacetylenedicarboxylate (378g, 2.66 moles) were charged to a 2L vessel. Toluene (750ml) was added and the mixture heated to reflux (oil bath temperature 145°C , diene dissolved $\geq 90^{\circ}\text{C}$). The reaction was refluxed for 20 h (overnight) before being cooled to room temperature. Evaporation of the toluene afforded a yellow/brown solid, which was recrystallised from 2-propanol to give 780g, 92.5% yield of the desired product as a white solid.

13


GC-MS gave a single peak m/z 348, HPLC 99.3%; ^1H NMR 3.54 (6H, s, 2 x CH_3), 4.47 (2H, s), 5.77 (2H, s), 7.24-7.34 (10H, m).

Synthesis of Terphenyl Cis-dimethylester, St2.




To a toluene (100ml) solution of the diene (stage 1 product, 10g, 28.7 mmol) was added palladium 10wt.% on activated carbon (1.5g, 10% wt). The reaction was refluxed (oil bath 130°C) for 20 h (overnight). The reaction was cooled slightly (80°C) and diluted with toluene (100ml) before hot filtering through a pad of celite filter agent. The filter cake was washed with a further 500ml hot toluene to remove all of the product. Cooling of the filtrate crystallised the desired product as a white solid 7.75g, 78%. GC-MS $\geq 95\%$, m/z 346; ^1H NMR 3.62 (6H, s, 2 x CH_3), 7.36-7.45 (10H, m), 7.52 (2H, s).

Synthesis of Terphenyl Cis diol, St3, St3B.



A solution of diester (10g, 17.56 mmol) in dichloromethane (130 mL) was added dropwise over 1 hour into a solution of diisobutyl aluminiumhydride (1M in hexane). After 2 h of stirring at room temperature the reaction was quenched, pouring the reaction mixture into a saturated solution of ammonium chloride. The desired product was extracted into dichloromethane (20mL MeOH added). The organic layer was dried (MgSO_4) and evaporated under vacuum affording 6.45 g (77% yield) of desired product. GC-MS confirmed 90% conversion to the diol and 10% of starting material remaining. ^1H NMR 2.925 (2H, OH), 4.78 (4H, s, CH_2OH), 7.34-7.46 (12H).


Synthesis of Cis indenofluorene, St5.



14


(2H, t, J 7.2), 7.39 (2H, t, J 7.2), 7.59 (2H, d, J 8.0), 7.82 (2H, s), 7.83 (2H, d, J 7.2); ^{13}C NMR 35.738, 118.954, 120.167, 125.374, 126.746, 127.089, 139.593, 141.057, 142.307, 143.306.

Synthesis of St5.




To a cooled (-78°C) solution of cis indenofluorene (2 g, 7.9 mmol) in THF (120 mL) was added BuLi (2.5M, 17.38 mmol). After addition was complete, the reaction mixture was left to stir at -78°C for a further 2 h and then left to warm to room temperature. The reaction mixture was then re-cooled to -78°C and octyl bromide (3.26 mL, 18.96 mmol) added. The reaction mixture was allowed to room temperature over night and the whole lithiation and alkylation process repeated. The reaction was poured onto a mixture of petroleum ether-Et₂O and washed with H₂O. The organic layer was isolated, dried (MgSO₄) and the excess octyl bromide/octane removed using Kugel distillation (40°C , 10^{-2} mbar). GC-MS indicated 81% dialkyl and 15% trialkylated product. The isolated mixed product (1.34g) was put through the lithiation-alkylation procedure again. To afford the desired tetra-alkylated product the whole experimental procedure was repeated using a further 5.2 equivalents of BuLi and 6 equivalent of octyl bromide. 1.069g of desired material was isolated and used crude in the next stage. ^1H NMR 0.4-1.4 (30H), 2.2 (2H, td, J 4.4, 12.8), 2.4 (2H, td, J 4.4, 12.8), 7.26-7.33 (6H, m), 7.70 (2H, d, J 7.6), 7.74 (2H, s); ^{13}C NMR 14.29, 22.84, 24.30, 29.68, 29.82, 30.32, 32.05, 40.88, 58.24, 119.05, 119.130, 121.78, 126.79, 127.24, 141.16, 142.30, 146.49, 150.98.

Synthesis of Monomer 1




To a 0°C solution of St5 (1.069g), iodine (catalytic) in CH₂Cl₂ (25 mL) was added a solution of Na₂CO₃ (0.387 g) in H₂O (6 mL). After stirring for 5 minutes, bromine (183 μL) was added dropwise. The reaction mixture was left to stir overnight. The reaction was treated with a 10% sodium thiosulphate solution (20 mL). The organic layer was removed, washed with water (2 x 20 mL). The organic layer was separated from the aqueous, dried (MgSO₄) and evaporated under vacuum. Column chromatography elute hexane gave 450mg of mono and di brominated product; confirmed by GC-MS. This mixture was subjected again to bromination.

Indenofluorene repeat units carrying substituents on the central phenyl ring of the repeat unit were prepared in accordance with the following scheme:




In addition to providing substituents on the central ring, the central ring of the monomer may comprise a fused ring, as illustrated below wherein the central ring is a benzothiadiazole. The first step may be performed by Suzuki coupling of the starting dibromo compound with two equivalents of a phenyl boronic ester.



16


Finally, cis-indenofluorene monomers carrying different substituents R¹-R⁴ were prepared in accordance with the following scheme. As shown in the scheme, asymmetric substitution at the 11 and 12 positions was accomplished by forming an amide as described in Weinreb, Tetrahedron Letters 22(39), 3815-3818, 1981; reacting the amide with one equivalent of a first alkyl, aryl or heteroaryl lithium to form a ketone; and reacting the ketone with one equivalent of a second alkyl, aryl or heteroaryl lithium that is different from the first alkyl, aryl or heteroaryl lithium.






Polymer Examples

Polymers according to the invention were prepared in accordance with the method set forth in WO 00/53656 by polymerisation of the monomers shown below. Boronic esters were derived from Monomer 1 in accordance with the method set forth in WO 00/53656.


Polymer 1







17

Polymer 2**Polymer 3****Polymer 4**

Polymer 5



For the purpose of comparison, polymers were prepared as per polymer 5 above except that the following trans-indenofluorene monomers were used in place of the cis-indenofluorene repeat unit according to the invention:

Polymer 6:**Polymer 7:****Polymer 8:****Polymer 9:**

Device Example

Onto indium tin oxide supported on a glass substrate (available from Applied Films, Colorado, USA) was deposited a film of poly(ethylene dioxythiophene) (PEDT / PSS), available from Bayer ® as Baytron P ®, by spin coating. The electroluminescent layer was formed over the layer of PEDT/PSS by spin coating from xylene solution comprising polymer 5 according to the invention. A bilayer cathode of calcium / aluminium was deposited over the electroluminescent layer and the device was encapsulated using an airtight metal enclosure containing a desiccant available from Saes Getters SpA.

For the purpose of comparison, identical devices were prepared except that comparative polymers 6, 7, 8 and 9 were used in place of polymer 5. Device performance for the devices prepared from these materials is summarised in Table 1 below.

Table 1

Polymer	CIE _x	CIE _y	V at 100 cd/m ²	Half life ¹ from 800 cd/m ²	Colour Shift ²	ΔV ³	% Burn- in ⁴
5	0.16	0.17	4.3	120h	0.03	1.0	3%
6	0.17	0.22	5.7	140h	0.06	2.8	12%
7	0.16	0.19	5.1	46h	0.04	0.2	24%
8	0.17	0.23	5.4	35h	0.02	0.0	20%
9	0.17	0.22	5.4	70h	0.06	0.6	1%

¹ Half-life = time taken for luminance to fall by half at constant current.

² Colour shift measured at half-life and taking into account the lateral CIE_x and CIE_y shift from the starting colours, measured as the square root of:

$$(\text{CIE}_x \text{ colour shift})^2 + (\text{CIE}_y \text{ colour shift})^2$$

³ Change in drive voltage during the half life of the device.


⁴ Burn-in refers to an initial fall in luminance when the device is driven followed by a more gradual decay in luminance.

As can be seen from Table 1, polymer 5 according to the invention provides the best performance across the range of parameters measured. For most parameters, polymer 5 is superior to the comparative polymers; for the remaining parameters, there is no instance where the performance of polymer 5 is significantly poorer than any of the comparative polymers.


Although the present invention has been described in terms of specific exemplary embodiments, it will be appreciated that various modifications, alterations and / or combinations of features disclosed herein will be apparent to those skilled in the art without departing from the spirit and scope of the invention as set forth in the following claims.

Claims

1. An oligomer or polymer comprising an optionally substituted first repeat unit of formula (Ir):



- wherein R^1 , R^2 , R^3 and R^4 , which may be the same or different, are independently selected from hydrogen or a substituent and two or more of R^1 , R^2 , R^3 and R^4 may be linked to form a ring.
2. An oligomer or polymer according to claim 1 wherein each R^1 , R^2 , R^3 and R^4 is independently selected from the group consisting of optionally substituted alkyl, alkoxy, aryl, or heteroaryl.
 3. An oligomer or polymer according to claim 1 or 2 wherein at least one of R^1 , R^2 , R^3 and R^4 is optionally substituted phenyl or optionally substituted C_{1-20} alkyl.
 4. An oligomer or polymer according to claim 3 wherein at least one R^1 , R^2 , R^3 and R^4 is different from at least one other of R^1 , R^2 , R^3 and R^4 .
 5. An oligomer or polymer according to any preceding claim wherein the first repeat unit is linked through the 2- and 9-positions.
 6. An oligomer or polymer according to any preceding claim wherein the oligomer or polymer comprises a second repeat unit.
 7. An oligomer or polymer according to claim 6 wherein the second repeat unit is selected from optionally substituted aryl, heteroaryl and triarylamine repeat units.
 8. An optionally substituted monomer of formula (Im):




wherein R^1 , R^2 , R^3 and R^4 , which may be the same or different, are independently selected from hydrogen or a substituent and two or more of R^1 , R^2 , R^3 and R^4 may be linked to form a ring; and each P represents a polymerisable group.

9. A monomer according to claim 8 wherein each P represents a leaving group capable of participating in a polycondensation mediated by a metal of variable oxidation state.
10. A monomer according to claim 9 wherein each P is independently selected from halogen; a moiety of formula $-O-SO_2-Z$ wherein Z is selected from the group consisting of optionally substituted alkyl and aryl; or a reactive boron group selected from a boronic acid, a boronic ester or a borane.
11. A process for preparing an oligomer or polymer comprising the step of oligomerising or polymerising a monomer according to any one of claims 8-10.
12. A process for preparing an oligomer or polymer according to claim 11 as dependent on claim 10 wherein each P is independently a halogen or a moiety of formula $-O-SO_2-Z$, and the monomer of formula (Im) is oligomerised or polymerised in the presence of a nickel complex catalyst.
13. A process for preparing a polymer according to claim 11 as dependent on claim 10 wherein the monomer of formula (Im) is oligomerised or polymerised with a second aromatic monomer in the presence of a palladium complex catalyst and a base and
 - a. each P is the same or different and comprises a reactive boronic group and the second monomer comprises two reactive groups independently selected from halogen and a moiety of formula $-O-SO_2-Z$, or
 - b. each P independently comprises a halogen or a moiety of formula $-O-SO_2-Z$ and the second monomer comprises two reactive boron groups which are the same or different
14. A process for preparing an oligomer or polymer according to claim 11 as dependent on claim 10 wherein one P is a reactive boron group and the other P is a halogen or a moiety of formula $-O-SO_2-Z$.
15. An optical device comprising an oligomer or polymer according to any one of claims 1-7.
16. An optical device according to claim 15 wherein the oligomer or polymer is located between a first electrode for injection of charge carriers of a first type and a second electrode for injection of charge carriers of a second type.
17. A switching device comprising an oligomer or polymer according to any one of claims 1-7
18. A field effect transistor comprising an insulator having a first side and a second side; a gate electrode located on the first side of the insulator; an oligomer or polymer according to any one of claims 1-7 located on the second


side of the insulator; and a drain electrode and a source electrode located on the oligomer or polymer.

19. An integrated circuit comprising a field effect transistor according to claim 18.
20. A method of forming an optionally substituted compound of formula (I):



(I)

comprising the step of eliminating LG-H from an optionally substituted compound of formula (Ip):



(Ip)

wherein each LG is the same or different and represents a leaving group.

21. A method according to claim 20 wherein each LG is hydroxy.
22. A method according to claim 20 or 21 wherein the elimination is performed in the presence of an acid.
23. A method according to claim 21 wherein the acid is polyphosphoric acid.
24. A method according to any one of claims 20-23 comprising the further step of providing a polymerisable group P on each of the outer phenyl rings of the compound of formula (I) or (Ip).

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
29 December 2004 (29.12.2004)

PCT

(10) International Publication Number
WO 2004/113412 A3

(51) International Patent Classification⁷: **C08G 61/02**,
C07C 25/22, H01L 51/30, C07C 1/20, 1/24

(21) International Application Number:
PCT/EP2004/006721

(22) International Filing Date: 22 June 2004 (22.06.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
03014042.0 23 June 2003 (23.06.2003) EP

(71) Applicant (for all designated States except US): **COVION
ORGANIC SEMICONDUCTORS GMBH** [DE/DE];
65926 Frankfurt am Main (DE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **WALLACE, Paul**
[GB/GB]; 11 Redwing Rise, Royston, Hertfordshire SG8
7XU (GB). **POUNDS, Thomas** [GB/GB]; 97 Arbury
Road, Cambridge CB4 2JD (GB). **O'DELL, Richard**
[GB/DE]; Jettenstetten 23, 84416 Taufkirchen (DE).
TOWNS, Carl [GB/GB]; Crown Cottage, 192 Silver
Street, Mountfitchet, Stansted, Essex CM24 8HB (GB).
McKIERNAN, Mary [GB/GB]; 12 Lee Close, Cottenham
(GB).

(74) Agents: **DÖRR, Klaus** et al.; Industriepark Höchst,
Gebäude F821, 65926 Frankfurt am Main (DE).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI,
SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

(88) Date of publication of the international search report:
21 April 2005

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: POLYMER

(57) Abstract: The present invention relates to new semiconductive oligomers and polymers, a process for their manufacture and their use in thin film electronic and optical devices, such as organic light emitting diodes (OLED) and photovoltaic devices, e.g. solar cells and photodetectors.

WO 2004/113412 A3

INTERNATIONAL SEARCH REPORT

International Application No

P/EP2004/006721

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08G61/02 C07C25/22 H01L51/30 C07C1/20 C07C1/24

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08G C07C H01L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, CHEM ABS Data, BEILSTEIN Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>PLUMMER B F ET AL: "STUDY OF GEOMETRY EFFECTS ON HEAVY ATOM PERTUBATION OF THE ELECTRONIC PROPERTIES OF DERIVATIVES OF THE NONALTERNANT POLYCYCLIC AROMATIC HYDROCARBONS FLUORANTHENE AND ACENAPHTHOL[1,2-k]FLUORANTHENE" JOURNAL OF THE AMERICAN CHEMICAL SOCIETY, vol. 115, 1993, pages 11542-11551, XP002271035 page 11542; figure I page 11544, right-hand column, last paragraph</p> <p style="text-align: center;">----- -/--</p>	8-10



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

° Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

18 October 2004

Date of mailing of the international search report

01 MAR 2005

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Schlicke, B

INTERNATIONAL SEARCH REPORT

International Application No

P/EP2004/006721

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	HARVEY R G ET AL: "NEW SYNTHETIC APPROACH TO POLYCYCLIC AROMATIC HYDROCARBONS AND THEIR CARCINOGENIC OXIDIZED METABOLITES" JOURNAL OF ORGANIC CHEMISTRY, vol. 65, no. 13, 2000, pages 3952-3960, XP002271036 Page 3954; Scheme 3; Compound 15	8
A	MÜLLEN K ET AL: "BRIDGING THE GAP BETWEEN POLYFLUORENE AND LADDER-POLY-p-PHENYLENE: SYNTHESIS AND CHARACTERIZATION OF POLY-2,8-INDENOFUORENE" MACROMOLECULES, vol. 33, 2000, pages 2016-2020, XP002271037 cited in the application the whole document	1-19
A	WO 00/53656 A (TOWNS CARL ROBERT ;DELL RICHARD O (GB); CAMBRIDGE DISPLAY TECH (GB) 14 September 2000 (2000-09-14) cited in the application abstract	1-19
A	WO 00/22026 A (KREUDER WILLI ;AXIVA GMBH (DE); BECKER HEINRICH (DE); SPREITZER HU) 20 April 2000 (2000-04-20) the whole document	1-19

INTERNATIONAL SEARCH REPORT

International application No.
PCT/EP2004/006721

Box II Observations where certain claims were found unsearchable (Continuation of item 2 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box III Observations where unity of invention is lacking (Continuation of item 3 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

see additional sheet

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☒ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

1-19

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

This International Searching Authority found multiple (groups of) inventions in this international application, as follows:

1. claims: 1-19

An oligomer or polymer comprising an optionally substituted first repeat unit of the formula Ir.

An optionally substituted monomer of the formula Im.

A process for preparing an oligomer or polymer comprising the step of oligomerising or polymerising a monomer of the formula Im.

2. claims: 20-24

A method of forming an optionally substituted compound of the formula I comprising the steps of eliminating leaving groups from the optionally substituted compound of the formula Ip.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

P/EP2004/006721

Patent document cited in search report		Publication date		Patent family member(s)		Publication date
WO 0053656	A	14-09-2000	AU	2926400	A	28-09-2000
			CA	2362459	A1	14-09-2000
			CN	1343225	T	03-04-2002
			EP	1165648	A1	02-01-2002
			WO	0053656	A1	14-09-2000
			JP	3310658	B1	05-08-2002
			JP	2002539287	T	19-11-2002
			US	2002095017	A1	18-07-2002
			US	6353072	B1	05-03-2002

WO 0022026	A	20-04-2000	DE	19846766	A1	20-04-2000
			AU	5743699	A	01-05-2000
			CN	1330670	T	09-01-2002
			DE	59908822	D1	15-04-2004
			WO	0022026	A1	20-04-2000
			EP	1123336	A1	16-08-2001
			JP	2002527553	T	27-08-2002
			US	6653438	B1	25-11-2003
